

300 Gen.Colin Powell Pkwy Phenix City,AL 36869

Telephone 800-554-7424 Fax: 334-664-3212

TextesT Repor 1266924
 Date: 4/3/14
 Page: 1 of 1

CLIENT: **FLAMEOFF COATINGS**
 2460 Mirror Lake Blvd.
 Villa Rica, GA 30180
 ATTN: Scott Soesbee

SAMPLE IDENTIFICATION: PET SILOUETTE PRINT 6.2 oz/sq.yd.
 TREATED WITH FlameOff Coating Fabric Protection

NFPA 701 (2010) TEST 1 FLAMMABILITY		Mass Before Test (grams)	Mass After Test (grams)	Mass Loss %	Drip Burn (Seconds)	After Flame (Seconds)
SPECIMEN *	#1	13.5	9.7	28.33	0.0	0.0
	#2	13.0	9.5	27.03	0.0	0.0
	#3	12.8	9.6	24.71	0.0	0.0
	#4	13.2	9.4	29.12	0.0	0.0
	#5	13.6	9.7	29.04	0.0	0.0
	#6	13.6	10.0	26.93	0.0	0.0
	#7	13.3	10.0	24.92	0.0	0.0
	#8	13.4	9.7	28.07	0.0	0.0
	#9	14.0	10.1	27.93	0.0	0.0
	#10	14.0	9.8	<u>29.71</u>	<u>0.0</u>	0.0
	Average			27.58	0.0	
	Avg. + 3 Std. Dev.			32.68		


* Specimens were conditioned at least 30 minutes at 105±5°C before testing.

CRITERIA: PASS/FAIL

MASS LOSS: 40% Max. Avg. or
 Avg. + 3 Standard Deviations Max. Ind.

DRIP BURN: 2 Seconds Max. Avg.

COMMENTS: The submitted sample passes the requirements of NFPA 701 (2010)
 Test 1 Flammability.

TEXTTEST


Signed by